



UCP

Primers

Universal Clear Primer for Wood

PRODUCT DESCRIPTION

UCP is the ideal bare wood primer for use before painting or varnishing. It can be used above and below water.

* Suited to both High Performance and Conventional varnishes.

* Bonds to the wood for excellent adhesion

The fast drying formulation is tougher and more durable than conventional primers.

PRODUCT INFORMATION

Colour	YPA600-Clear
Finish	Gloss
Specific Gravity	1.1
Volume Solids	50%
Typical Shelf Life	2 yrs
VOC (As Supplied)	467 g/ltr
Unit Size	375 ml

DRYING/OVERCOATING INFORMATION

Drying

	5°C	15°C	23°C	35°C
Touch Dry [ISO]	5hrs	4hrs	3hrs	2hrs

Overcoating

Substrate Temperature

Overcoated By	5°C		15°C		23°C		35°C	
	Min	Max	Min	Max	Min	Max	Min	Max
Perfection Undercoat	24hrs	36hrs	12hrs	28hrs	6hrs	24hrs	4hrs	16hrs
Perfection Varnish	24hrs	36hrs	12hrs	28hrs	6hrs	24hrs	4hrs	16hrs
Primocon	24hrs	36hrs	12hrs	28hrs	6hrs	24hrs	4hrs	16hrs
UCP	24hrs	36hrs	12hrs	28hrs	6hrs	24hrs	4hrs	16hrs
Yacht Primer	24hrs	36hrs	12hrs	28hrs	6hrs	24hrs	4hrs	16hrs

Note: If maximum overcoating time has been exceeded, sand using 80-180 grade (grit) paper. All international varnishes are compatible with UCP and can be applied using the overcoating time observed for Perfection varnish.

APPLICATION AND USE

Preparation	BARE WOOD: Sand smooth with 80-180 and then 280 grade paper. Clean surface by brushing, dusting or wiping. If wiping with solvent allow to dry completely before applying first coat.
Method	Contains Isocyanates which may be harmful to lungs, read the health and safety data section before use. Avoid a 'bitty' finish by applying only on clean dry timber. Do not exceed recommended film thickness or bubbling may occur.
Hints	<p>Thinner YTA006 Thinners No.9</p> <p>Cleaner YTA006 Thinners No.9</p> <p>Ventilation and Humidity Control The minimum humidity is 35%, drier conditions than this will retard curing.</p>

Some Important Points	DO NOT SPRAY. Do not use in conjunction with Intertox. Do not use below 5°C. Ambient temperature should be minimum 5°C/40°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/40°F and maximum 35°C/95°F. Product temperature should be minimum 5°C/40°F and maximum 35°C/95°F.
Compatibility/Substrates	Can be overcoated with all varnishes in International range. Not suited to oily timbers such as Teak and Iroko. On oily timbers such as Teak use Perfection for Teak or thinned varnish instead of UCP.
Number of Coats	1-4 as per specification
Coverage	(Theoretical) - 20.00 (m ² /lt) (Practical) - 17.50 (m ² /lt)
Recommended DFT	25 microns dry
Recommended WFT	50 microns wet
Application Methods	Brush, Roller

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage	<p>GENERAL INFORMATION: Exposure to air and extremes of temperature should be avoided. For the full shelf life of UCP to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight.</p> <p>TRANSPORTATION: UCP should be kept in securely closed containers during transport and storage.</p>
Safety	<p>GENERAL: Contains isocyanates which may be harmful to the respiratory tract. Read the label safety section for Health and Safety Information, also available from our Technical Help Line.</p> <p>DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.</p> <p>Remainders of UCP cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.</p>

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

X and International are registered trademarks of Akzo Nobel.

Regional Addresses

Head Office
International Paint Ltd
P O Box 20980
Oriol House
16 Connaught Place
London W2 2ZB
United Kingdom
tel: +44 (0) 171 479 6000
fax: +44 (0) 171 479 6500

European Region
International Paint Ltd
Stoneygate Lane
Felling, Gateshead
Tyne & Wear NE10 0JY
United Kingdom
tel: +44 (0) 191 469 6111
fax: +44 (0) 191 438 3977

Asia Region
International Paint Singapore
(Pte) Ltd
449 Tagore Industrial Avenue
01-03 Hong Joo Industrial
Building
Singapore 787820
tel: +65 6453 1981
fax: +65 6453 1778

Australasia Region
International Paint
115 Hyde Road
Yeronga, Brisbane
Queensland 4104
Australia
tel: +61 (0) 7 3892 8866
fax: +61 (0) 7 3892 4287

North America Region
International Paint Inc
2270 Morris Avenue
Union
New Jersey 07083
USA
tel: +1 (0) 908 686 1300
fax: +1 (0) 908 686 8545

South America Region
International Paint
Rod Rap tavares, KM 18.5
Predio Administrativo 11
Butanta CEP 05577-300
Sao Paulo, Brazil
tel: +55 (0) 11 3789 2000
fax: +55 (0) 11 3789 2200



Ref: 05000027
Issue Date: 1-Mar-2003
Supersedes: 14-Feb-2003